



Product description	SH7575U is a bakery mold base silicone rubber compound. It can be used with various color and heat cured after the peroxide curing agent
Applications	Various bakery mold
Key performance properties	– Excellent process ability – Easy production of color and quartz – Good heat stability

Typical Property Data

Benefits	– Excellent process ability – Easy production of color and quartz – Good heat stability			
Typical properties	Properties	Test Method	Unit	SH7575U
	Appearance	ASTM E1767	–	Transparency
	Williams Plasticity	ASTM D926	–	270
	Curing Condition	Curing Agent	–	1) KC-8
		Amounts	Phr	0.5
		Press 1st Cure	–	170°C 10min
		Oven 2nd Cure	–	200°C 4hr
	Specific Gravity	ASTM D792	–	1.20
	Hardness	ASTM D2240	Shore A	76
	Tensile Strength	ASTM D412	MPa	9.5
	Elongation	ASTM D412	%	400
	Tear Strength	ASTM D624C	N/mm	36.0
		ASTM D624B		17.9
	Linear Shrinkage	JIS K6249	%	4.2
1) KC-8 : 2,5-dimethyl 2,5-di(t-butyl peroxy) hexane 45 % paste ※ Typical properties should not be used as specifications They are evaluated in laboratory, and can be differ from test condition.				
Composition	– Silicone polymer – Silica			
How to use	For blending or coloring, milling with two-roll mill is the most suitable process. Milling time should be carefully decided to secure uniformity of materials.			
Features	– Bakery mold base silicone rubber			

Storage and packaging

Shelf life and storage	– Use it within 12 months from the date of manufacture. – Keep out of the reach of the children.
-------------------------------	---

	- During transportation, try to avoid direct sunlight. Conditions of under 30°C with shade is commended. - If store condition is not fulfilled, the products' lifetime may be affected. Also, deterioration of the products' quality within shelf life time may occur.
Packaging	20 kg box, 480kg box
Remarks	
Handling	- Wear eye protection and protective gloves when handling this product.
Precautions	- Material Safety Data Sheets are available upon request from KCC.
Limitation	The featured product must be checked prior to use. 1) If applying to other purposes, defects can be generated. 2) If using non-suggested curing agents, its own properties can be altered. 3) If mixing with other products, degradation of properties and defects can be caused. 4) Additives or pigments must be used under technical support of KCC. 5) If it's first use, product must be applied after technical suggestion and assistance of KCC. Any other inquiries or methods of use can be found on KCC webpage and enquired technical support team at KCC.
Warranty information	Please read carefully This TDS is considered to be accurate. KCC's guarantee of the product will apply, only if conditions on TDS (limitation, notice, application) are fulfilled within expiry date. If not, KCC cannot guarantee the quality of the product. KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted. KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.
1'st issue	2009-03-01
Revision	2015-08-01

※ Please refer to MSDS if you want to know more specific usage or caution.
for further information, please see our website, www.kccworld.co.kr

