



Technical Data Sheet

Korepox EH2360 (Two-Component)

Product Description	A two-component, polyamine cured pure epoxy resin based self-priming, anti-abrasion coating with excellent resistance to seawater, crude oil, fuel oil and abrasion. Applicable over new or old steel requiring only the removal of loose rust as a surface tolerant coating, workable at low temperature even -18 °C/-0.4 °F and meets VOC requirements as high solids coating.
Packing	Korepox EH2360 is supplied as two separate packages. -. Base (Part A) and Curing agent (Part B) in the correct proportion for the mixture. Do not open package until use. Each package (Base and Curing agent) must be used entirely for mixing to ensure the mixing ratio. Left-over material in the packages cannot be used.
Recommended Use	As an anti-corrosion and anti-abrasion coating for long-life protection of steel structures in severely corrosive environment such as Underwater hull outside, Boottop, Topside, Exposed parts of ship, Water ballast tank, Cargo holds, etc. As a tank coating for ship's crude oil tanks, fuel oil tanks and interior of pipe lines transfer crude oils, etc. Applicable to steel structures for offshore projects, plants, bridges and others. For application in water ballast tanks at newbuilding stage in accordance with PSPC (IMO Res. MSC.215(82), see the "Technical Information for PSPC Applications-Korepox EH2360"

Physical Properties

Finish and Color	1151(Greyish yellow), 1128(French grey)
Solids by Volume	Approx. 74 % (Determined by ISO 3233)
Specific Gravity	Approx. 1.50 for Mixture of Base and Curing agent.
Flash Point	Base (EH2360PTA) : 26°C / 79°F (Closed cup) Curing Agent (EH2360PTB) : 26°C / 79°F (Closed cup)

Application Details

Surface Preparation	Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc. - Blast cleaning to Sa2½ or power tool cleaning to St3, etc. - Profile requirements : 30 ~ 75 μm in case of full or partial blast cleaning.
Application Condition	The surface should be adequately cleaned and dried. Do not apply when relative humidity is above 85 %. The surface temperature should be at least 3 °C (5 °F) above dew point to prevent condensation. In confined areas, ventilate with clean air during application to assist solvent evaporation. Temperature during application and curing is preferable from -18°C / 0°F to 49°C / 120°F. This temperature condition is for the substrate and surrounding air.
Mixing	EH2360PTA (Part A, Base) : EH2360PTB (Part B, Curing agent) = 6 : 1 (by volume) - Mix with supplied mixing ratio only. Do not vary or subdivide. - Before mixing, shake or stir the Base very thoroughly. - Pour the curing agent into the Base with constant mechanical stirring. Do not mix in reverse order. Continuous stirring until mixture is free of lumps

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

Technical Data Sheet

Korepox EH2360 (Two-Component)

Application	Spray	: Airless or Air spray
	Brush and Roller	: Recommended for small area and stripe coating for specified edges, welds, hard to reach areas, etc.
	For airless spray application ;	
	Nozzle orifice	: 482 μm ~ 787 μm (0.019" ~ 0.031")
	Fan	: 40° ~ 60°
	Output pressure	: 11.7 MPa ~ 15.2 MPa
	Airless Pump Ratio	: 45 : 1 ~ 73 : 1
	(Airless spray data are indicative and subject to adjustment)	

Recommended Coating System	■ For Water Ballast Tanks
	1 st Coat : Korepox EH2360 (1151, 160 μm DFT / 216 μm WFT)
	2 nd Coat : Korepox EH2360 (1128, 160 μm DFT / 216 μm WFT)

-. Depending on the purpose and the area of use, different film thickness may be applied.

Thinning	Product Name	: Thinner No. 024 or Other thinner approved by KCC
	Thinning Ratio	: 5% ~ 10% (by volume)
	* Do not dilute each component separately.	

Typical Film Thickness	(Per Coat)	Typical	Minimum	Maximum
	Dry Film Thickness (μm)	160	75	*
	Wet Film Thickness (μm)	216	101	*
	Theoretical Spreading Rate (m^2/L)	4.63	9.87	*
* Max. total 2,000 μm dry (as guideline of coating application. For more detailed information, consult with TSD (Technical Service Department) in KCC)				

Drying Time & Recoating Interval	Substrate temperature	5°C / 41°F	10°C / 50°F	20°C / 68°F	30°C / 86°F
	Dry to touch	8 h	3 h	1 h	0.5 h
	Dry to walk on	16 h	8 h	3 h	3 h
	Dry to hard	16 h	8 h	3 h	3 h
	Dry to recoat (Full / Min.)	16 h	8 h	3 h	3 h
	Dry to recoat (T/up / Min.)	16 h	8 h	3 h	2 h
	Dry to recoat (Max.)	7 d	7 d	7 d	7 d
	Dry to immersion (Full)	8 d	7 d	3 d	3 d
	Dry to immersion (T/up)	5 d	4 d	1.5 d	1 d

* d : days, h : hours, Full : Full coat application, T/up : Touch-up application.

* These are the results from laboratory tests done under standardized conditions. Thus, actual times may be different due to environment situations such as weather, wind and humidity, etc.

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

Technical Data Sheet

Korepox EH2360 (Two-Component)

Ventilation	Adequate ventilation with clean air should be maintained during application and curing to assist solvent evaporation.
Cleaner	Thinner No. 024 or Tool cleaner 009
Pot Life	3 h at 20°C / 68°F Pot life may be shorter under higher temperature and humid conditions.
Preceding Coat	According to specification.
Shelf Life	12 months
Standard Packing Unit	16 L (EH2360PTA : 13.7 L, EH2360PTB : 2.3 L)
Safety Precautions	Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.
Manufacture	KCC Corporation 1234, Bangeo-dong, Dong-gu, Ulsan, Korea
Issued	August 2009, Rev.06

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.



KCC Corporation