



A chlorinated rubber based antifouling paint containing cuprous oxide providing very effective and extended protection against fouling.

Approved as TBT-free antifouling paint by Korean Register of Shipping (KR), Russian Maritime of Shipping(RMRS)

Recommended use	General purpose antifouling paint, keel to load line, on vessels in global trade, with extended docking interval.
------------------------	---

Physical Properties

Finish and Color	Flat. Red Brown, Dark Brown
Specific gravity	Approx. 1.40
Solids by volume	Approx. 48 % (Determined by ISO 3233)
Spreading rate (Theoretical)	3.84 m ² /L in 125 μm dry film thickness on a smooth surface.
Flash point	26 °C /79 °F (Closed cup)

Application details

Surface preparation	Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.
Preceding coat	Korabor Aluminium H.B. RH248, Kovinyl Sealer VH137AL, Korepox H.B. EH2560 or according to specification. * Tar bleeding may occur from Korepotar H.B. EH173(S), etc. This effect is only cosmetic problem and has no negative influence on the antifouling performance. * Renewal : High pressure fresh water hosing to remove salt deposits and other contaminants. Allow surface to dry before recoating with Korabor A/F740.
Method of application	Spray (Airless or Air), Roller or Brush application. For airless spray application : Nozzle orifice: 635 μm ~ 787 μm (0.025" ~ 0.031") Output pressure: 13.8 MPa ~ 19.7 MPa Fan: 60 ° (Airless spray data are indicative and subject to adjustment)
Thinning	Thinner No. 002
Application conditions	The surface should be cleaned and dried completely. Do not apply when relative humidity is above 85 %. The surface temperature should be at least 2.7 °C (5 °F) above dew point to prevent condensation. In confined areas, ventilate with clean air during application to assist solvent evaporation.
Film thickness	125 μm dry. Two (2) or Three (3) coats are recommended with different color of consecutive coats. Depending on the purpose and the area of use, different film thickness may be applied. This will alter spreading rate and may influence drying time and recoating interval.

Drying time	Substrate temperature	5 °C /41 °F	20 °C /68 °F	30 °C /86 °F
	Set to touch	8 h	2h	2h
	Dry through	24h	12h	8h
	* The actual drying time is subject to the film thickness, ventilation, humidity etc., and drying time under other temperature conditions should be checked and informed by KCC			
Recoating interval	At 20 °C /68 °F, Minimum : 6 h Maximum : Free Before overcoating, remove any oil, salt, chalking material and any other contaminants on aged coating film completely by proper cleaning method such as solvent cleaning and/or fresh water washing.			
Storage and package				
Shelf life	12 months			
Packing Unit	15 L, 18 L			
Remarks				
Note	Avoid contact with skin and inhalation of paint mist or solvent vapor. In case of eye contact, the eyes should be rinsed immediately by fresh water continuously for at least 15 minutes. Doctor’s advice is recommended. In case of skin contact, the exposed area should be cleansed thoroughly with soap and water. Contaminated clothing should be removed and laundered with soap and water before reuse. In case of ingestion, swallow promptly a large quantity of milk, egg white or gelatin as a first aid. (If these are not available, drink a large quantity of water instead.) And obtain immediate medical attention.			
1'st issue	2011-07-01			
Revision	2016-11-17			

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

