



KOREPOX PRIMER EP1160 is a two-component, epoxy resin based primer with excellent adhesion, durability, resistance to water, abrasion and chemicals.

Recommended use	As a primer in hammertone coating system.
------------------------	---

Physical Properties

Finish and Color	Flat. Beige, Gray
Specific gravity	1.2 ~ 1.4 (Kg/L) according to color
Solids by volume	Approx. 47%
Spreading rate (Theoretical)	13m ² /L in 40 micron dry film thickness on a smooth surface.
Flash point	28°C/82°F (Closed cup)

Application details

Surface preparation	Remove any rust, dirt, oil and other contaminants from surface to be coated with suitable cleaning method. * Chemical conversion treatment is recommendable
Preceding coat	GALVANY SHOPPRIMER IZ182 or according to specification
Method of application	Air spray application. Nozzle orifice : 1.3 ~ 1.5mm Output pressure : 4 ~ 5Kg/cm ² Number of spray : 4 ~ 5 times (going and coming) (Air spray data are indicative and subject to adjustment.) * Roller or Dipping is not recommendable.
Thinning	* For air spray application, use THINNER No. 053, 024 Adjust the viscosity up to 18~22 sec. in Ford cup No.4 at 20°C/68°F (Thinning rate : 25~35% by volume). But, it may be changed by application condition and environment, etc. * Use well strained paint. * Only use specified THINNER.
Application conditions	The surface must be completely clean and dry. Preferred temperature during application is 15~25°C/59~77°F, and relative humidity is 35 ~ 80%. The surface temperature must be at least 3°C (5°F) above dew point to prevent condensation.
Film thickness	Recommended per coat 30 ~ 40 microns dry
Drying time	At 20°C/68°F, Set to touch : 20 minutes Dry through : 8 hours
Subsequent	

Coat	According to specification
Pot life	At 20°C/68°F , 8 hours
Heat resistance temperature	Continuous : 120°C/248°F Non-Continuous : 150°C/302°F
Storage and package	
Shelf life	12 months
Storage	Store in cool, dry, well-ventilated place. Can of bottom composition should be turned regularly twice a month
Packing Unit	16ℓ (Base : Curing Agent = 12.8ℓ : 3.2ℓ)
Remarks	
Note	Avoid humidity and direct sunlight. Mix thoroughly prior to application. Keep containers closed when not in use. Keep away from sparks and open flames. Avoid prolonged breathing of solvent vapors and contact with skin and eyes. In case of eyes contact, flush immediately with plenty of water for at least 15 minutes. Use with adequate ventilation. Respiratory protection is recommended when spraying this material in confined space or stagnant air.
1'st issue	2011-09-01
Revision	

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

