



Korethane enamel UT5561(HD) is a two-component, acrylic polyurethane resin based finish coating with excellent color and gloss retention, workability and durability. Especially, it is rust-preventing primerless top coat so does not need primer coating. It provides a tough film having outstanding resistance to chemical and weathering.

Recommended use	As a topcoat for use on heavy-industrial equipment, tank, container and the general steel appliance, etc.
------------------------	---

Physical Properties

Finish and Color	Semi gloss. Colors are depending on KCC's standard color card, and other colors are available on request.
Specific gravity	Approx. 0.9 ~ 1.3 (kg/ℓ).
Solids by volume	Approx. 38%
Spreading rate (Theoretical)	8.5㎡/ℓ in 45 microns dry film thickness on a smooth surface.
Flash point	23℃ ~ 32℃ / 73°F ~ 89°F (Closed cup)

Application details

Surface preparation	For repair work : Sand the failure areas of paint film cleanly, and allow to dry thoroughly. For new work : Remove any dust, oil , grease and other impurities from the surface to be coated and allow to dry completely.
Method of application	Air spray application. Nozzle orifice : 1.3 ~ 1.5 mm Output pressure : 4 ~ 5 atm (Above air spray data are indicative and subject to adjustment). Use the well strained paint.
Thinning	Thinner No. ZY0404 or 0278(HD)(Thinning ratio : 20 ~ 30%). Adjust the paint viscosity up to 16 ~ 20 seconds in Ford Cup No. 4.(Air Spray) Do not dilute components separately, only the mixture.
Application conditions	Preferred, temperature during application is 25℃/77°F, and relative humidity preferably below 85%.
Film thickness	Recommended per coat 40 ~ 50 microns dry. 2 ~ 3 coats are recommendable.
Drying time	At 20℃/68°F, Set to touch : Approx. 20 minutes Dry hard : Approx. 4 hours Fully cured : Approx. 7 days Force drying : 80℃/ 176°F x 30 minutes
Pot life	Approx. 4 hours (at 20℃ / 68°F, 40% diluted)
Recoating interval	At 20℃/68°F, MIN. 4 hours

Storage and package

Packing Unit	13.7L
---------------------	-------

Remarks	
Note	Protect skin and eyes, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Keep the recommended film thickness at application. Thick film per coat may result in bubbling defect. Clean tools immediately after use.
1'st issue	2013-07-01
Revision	2016-05-24

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience.

However, there are many factors affecting the performance of product and the product quality itself,

so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing.

We reserve the right to change the data without notice and you

should check that this data sheet is current prior to using the product.

