

<b>Product description</b>	KORESEAL SL886 is a neutral cure silicone sealant designed for secondary sealant in insulating glass units of residential building
<b>Applications</b>	Secondary sealant in insulating glass units of residential building
<b>Key performance properties</b>	*1-COMPONENT & NON-SLUMP *Good Adhesion to most substrates *Outstanding physical properties (High-modulus)
<b>Certifications</b>	KS F4910 G-25HM Korea Eco-Label

**Typical Property Data**

<b>Benefits</b>	<ul style="list-style-type: none"> <li>- Excellent weatherability</li> <li>- Room Temperature Cure</li> </ul>
-----------------	---

<b>Typical properties</b>	- Tested at 23 °C, 50 % relative humidity		
	Property	Unit	Result
	Binder	-	Silicone Polymer
	Curing System	-	Neutral curing (Oxime)
	Color	-	Black
	Consistency	-	Soft paste
	Solvent	-	NONE
	Tack free time	min	Max. 10
	Specific Gravity	-	1.41 ± 0.1
	Hardness	Shore A	APPROX. 30
	Tensile Strength (ASTMD412)	N/mm <sup>2</sup>	APPROX. 1.0
	Elongation (ASTMD412)	%	APPROX. 400
	Packaging	-	0.5 L AL SSG
	Shelf Life	Month	12
	Weathering resistance	-	Excellent
* ASTM American Society for Testing and Materials			
<b>Notice</b> 1) These property values are tested in a lab condition. They might be changed by testing and storage conditions.			
2) Please contact to KCC sales office before writing specifications on this product.			

<b>Composition</b>	Silicone Polymer
--------------------	------------------

<b>How to use</b>	<p><b>1) CLEAN ALL JOINT SURFACE</b></p> <p>Clean all substrate surface and regarding dust oil, frost and any contaminants Wipe polluted parts using solvent and a piece of cloth. Do not use detergent, soap and water.</p> <p><b>2) APPLYING SEALANT</b></p> <p>Applying sealant deeply into joint. Sealant must be filled into the joint cavity perfectly.</p> <p><b>3) TOOL SEALANT</b></p>
-------------------	---

Tool sealant immediately after sealant application. It helps to provide smooth and flat finish and to ensure that the sealant wets the sides of the joint without any voids.

**4) CLEANING**

Clean all stuffs around sealant cure area and do not touch when sealant is curing.

**5) Curing**

In curing of sealant, protect from dirt and other contaminating materials.

Before full cure of sealant, do not touch and impact to sealant.

<b>Features</b>	<ul style="list-style-type: none"> <li>*1-Component</li> <li>*Excellent gunability</li> <li>*Neutral cure</li> </ul>
-----------------	--

**Storage and packaging**

<b>Shelf life and storage</b>	<ul style="list-style-type: none"> <li>- Use it within 12 months from the day of manufacture. As change in quality can be possible at long term storage use in validity.</li> <li>- Store in a cool dry place out of direct sunlight.</li> <li>- Keep in place that child's hand does not touch and never ingest or do not touch in skin.</li> <li>- Don't work at neighborhood of heat or fire.</li> <li>- Store in original unopened containers in a dry place. Temperature should not exceed 25 °C for prolonged periods. (Recommended at 5 ~ 25 °C)</li> <li>- Please, refer product MSDS for more details regarding safety information.</li> </ul>
-------------------------------	---

<b>Packaging</b>	500 ml Aluminum Foil Sausage, 20pcs/Box
------------------	---

**Remarks**

<b>Handling</b>	* Check the Spacers properly aligned . It controls the sealants depth
<b>Precautions</b>	<ul style="list-style-type: none"> <li>* Clean all joint surface (Clean all substrate surface removing contaminants )</li> <li>* Primer may be needed for optimum adhesion to some substrate surface based on adhesive testing. Information on KCC primer is available on request from KCC</li> <li>* Corner Keys must be dry and clean</li> <li>* Spacers must be dry and clean</li> <li>* Coated glass or Low-e glass is required edge stripping</li> <li>* Poly isobutylene seal must be applied continuously</li> <li>* Store in original unopened containers in a dry place. Temperature should not exceed 25 °C for prolonged periods. (Recommended at 5 ~ 25 °C)</li> <li>* Use at room temperature in the range of 30 to 80 % relative humidity.</li> <li>* It is recommend to work at temperature 10°C to 30°C</li> <li>* Time for complete cure is depend on the thickness of sealant applied.</li> <li>* Adhesion may decline in case of the substrate contaminated. For the best adhesion, clean surfaces thoroughly with solvent before applying the product.</li> <li>* Wear eye protection and protective gloves when handling this product.</li> <li>* Maintain adequate ventilation in the work place at all times.</li> <li>* Keep in place that child's hand does not touch and never ingest or do not touch in skin</li> <li>* Keep or do not work at neighborhood of heat or fire.</li> <li>* Keep cure time until product is fully cured.</li> <li>* Do not use besides service.</li> <li>* Do not inflict shock in receptacle.</li> <li>* Avoid direct ray of light and keep in state that is tightly shut in place that moisture is less.</li> <li>* Do not mixing with other products.</li> <li>* Wash your skins cleanly after work.</li> <li>* Abolish through waste processing company.</li> <li>* As change in quality can be at long term storage, use in validity.</li> <li>* Do not use defected back-up materials. It might induce air bubble.</li> </ul>

	<p>Confirmation is necessary in regard of Sealant before use.</p> <ul style="list-style-type: none"> <li>- Apply after adhesion and compatibility test although adhesion of sealant is excellent to most of building materials.</li> <li>- Sufficient tests are needed for purposed applications. The applicability of sealant is depend on the decision of customer.</li> </ul> <p>※ Inquire other questions to customer service.</p> <p>※ When there is something wrong to product, it can be compensated by compensation regulation.</p>
<b>Limitation</b>	<p>SL886 should not be applied :</p> <ol style="list-style-type: none"> <li>1) To building materials of adhesive hindrance or discoloration that bleed oil, plasticizer or solvent and so on.</li> <li>2) In totally airtight spaces.</li> <li>3) When substrate surface temperatures exceed 50 °C and under 5 °C.</li> <li>4) To wet surface (on frost-laden or damp surfaces).</li> <li>5) Humid day(over 85% relative humidity day).</li> <li>6) For continuous immersion in water or in below-grade applications.</li> <li>7) Surface in direct contact with food.</li> <li>8) For continuous high pressure and high temperature.</li> <li>9) Interior fire prevention section.</li> <li>10) Joint region that where is expected by physical friction.</li> <li>11) Region that paint is required to sealant.</li> <li>12) Not recommended for use on polycarbonate plastic sheeting, self-cleaning glass, non-staining fluorine coating suitability for use on other type of plastic should be tested prior to application.</li> <li>13) Structural glazing</li> <li>14) Low-E glass without edge stripping.</li> <li>15) limited bite joint status (min : 3mm , Max: 14mm)</li> <li>16) Do not use with incompatibility materials</li> </ol>
<b>Warranty information</b>	<p>The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KCC's products are safe, effective, and fully satisfactory for the intended end use.</p> <p>KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted.</p> <p>KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages.</p> <p>Suggestions of use shall not be taken as inducements to infringe any patent.</p>
<b>1'st issue</b>	2014-12-23
<b>Revision</b>	2021-07-13

※ Please refer to MSDS if you want to know more specific usage or caution. for further information, please see our website, [www.kccworld.co.kr](http://www.kccworld.co.kr)