



Product description	SL7260AB-M is a two-component liquid silicone rubber for general purpose. (Mixing ratio – A : B = 1 : 1 (by weight))
Applications	General purpose
Key performance properties	Suitable for LIMS(Liquid Injection Molding System) because of the similar viscosity of A part and B part No by-products because of addition curing LSR Excellent transparency and physical properties after curing

Typical Property Data

Benefits	– Long pot-life					
	– Rapid curing rate					
	– Excellent release					
Typical properties	Properties			Test method	Unit	Press 1st cure 2)
	Before curing	Appearance	PTA	ASTM E 1767	–	Translucent
			PTB			Translucent
		Viscosity 1)	PTA	ASTM D 4287	Pa.s	200
			PTB			200
	Mixing ratio(by weight)					1 : 1
	After curing	Pot life(25℃, Day)				3
		Appearance		ASTM E 1767	–	Translucent
		Curing time(120℃, T60)		ASTM D 5289	sec	45
		Specific gravity (at 25℃)		ASTM D 792	–	1.12
		Hardness		ASTM D 2240	Shore A	58
		Tensile strength		ASTM D 412	MPa	8.5
		Elongation		ASTM D 412	%	400
		Tear strength		ASTM D 624 B	N/mm	40
	1) Shear Rate 10 s–1					
	2) Sheet curing conditions : press cure at 170℃/10 min					
	Caution) Typical property data values should not be used as specifications					
Composition	– Silicone polymer					
	– Silica					
How to use	For making a suitable product, Mix components A and B in the ratio 1 : 1(by weight)					
Features	– High temperature vulcanizing and addition curing LSR					

Storage and packaging

Shelf life and storage	Use it within 12 months from the day of manufacture. Store in a cool dry place out of direct sunlight. Keep out of the reach of the children.
Packaging	PART A : 20 kg Straight PE Pail, 200 kg Straight Drum

Remarks	
Handling	Wear eye protection and protective glove when handling this product.
Precautions	May cause a curing difficulty with amine, sulfur, organicphosphate compound, and organicmetallic compound.
Warranty information	Please read carefully The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KCC's products are safe, effective, and fully satisfactory for the intended end use. KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted. KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.
1'st issue	2008-04-29
Revision	2018-01-02

※ Please refer to MSDS if you want to know more specific usage or caution.
for further information, please see our website, www.kccworld.co.kr

