



## Korepolar EH3090 (Two-Component) -

### Product Description

Korepolar. EH3090 is a high solids, two-component, epoxy resin based coating, designed for ice-going vessel. Excellent impact resistance, abrasion resistance. Also, it provides a hard and tough film with long term durability and meets VOC regulation.

### Recommended Use

As a coating for corrosion protection of ice-going vessels including ice breakers.  
(EH3090's abrasion and impact resistance makes it an excellent coating for the ice-belt of vessels in arctic waters.)

## Physical Properties

**Finish and Color** Gloss. Black, Red

### Drying Time

Substrate temperature	10°C/50°F	20°C/68°F	30°C/86°F
Set to touch	8 h	3 h	2 h
Dry through	36 h	15 h	8 h

The actual drying time is subject to the film thickness, ventilation, humidity etc., and drying time under other temperature conditions must be checked and informed from us.

### Overcoating Data

Dry to recoat	10°C/50°F	20°C/68°F	30°C/86°F
Minimum	8 h	3 h	2 h
Maximum	10 d	7 d	4 d

Prior to overcoating, remove the oil, salt, chalking material and any other contaminants on aged coating film completely by proper cleaning method such as solvent cleaning and/or fresh water washing.

**Solids by Volume** Approx. 98% (Determined by ISO 3233)

**Theoretical Spreading Rate** 1.96 m<sup>2</sup>/L in 500 μm dry film thickness on a smooth surface.

**Specific Gravity** Approx. 1.4 ~ 1.6 for Mixture of Base and Curing agent.

**Flash Point** Base (EH3090-A) : 32 / 90°F (Closed cup)  
Curing Agent (EH3090-B) : 63 / 149°F (Closed cup)

## Application Details

**Surface Preparation** Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.  
\* Blast cleaning to minimum Sa2.5 (ISO 8501 1:1988), blasting profile (Rz) 30~ 70 μm.

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.



## Korepolar EH3090 (Two- Component)

---

<b>Application Conditions</b>	<p>The surface must be completely cleaned and dried.</p> <ul style="list-style-type: none"><li>* Apply by hot twin airless spray only. Prior to application, bring both components and the mixed paint to between 45 °C ~50 °C by recirculation and the use of insulated lines.</li><li>* Use only where application and curing can proceed at temperature above 10 °C/50 °F and at relative humidity below 85%.</li><li>* The surface temperature must be at least 2.7 °C (5 °F) above dew point to prevent condensation.</li><li>* Storage must be between 20~30 °C (68~86 °F) to ensure suitable application viscosity.</li><li>* Paint application should be carried out the ambient and surface temperature conditions of over 10 °C/50 °F. After application the curing temperature must be at least above 5 °C/41 °F to avoid film defects due to slow drying.</li><li>* Keep the temperature specified for application and curing.</li></ul>								
<b>Mixing</b>	<p>Base (EH3090-A) : Curing Agent (EH3090-B) = 2 : 1 (by volume) Mix thoroughly together prior to application in the proportions with power agitator as delivered.</p>								
<b>Thinning</b>	<p>Thinner No.024 or Other thinner approved by KCC up to 3%. (If necessary) But Thinning will destroy the abrasion resistance properties of the coating Do not dilute each components separately .</p>								
<b>Application Method</b>	<p>Hot twin feed Airless Spray, Brush application. For airless spray application ;</p> <table><tr><td>Pump ratio</td><td>: Min. 66:1</td></tr><tr><td>Nozzle orifice</td><td>: 482.6 μm ~ 787.4 μm (0.019" ~ 0.031")</td></tr><tr><td>Output pressure</td><td>: 26.4Mpa ~ 46.8Mpa</td></tr><tr><td>Fan</td><td>: 40° ~ 65 °</td></tr></table> <p>(Airless spray data are indicative and subject to adjustment)</p>	Pump ratio	: Min. 66:1	Nozzle orifice	: 482.6 μm ~ 787.4 μm (0.019" ~ 0.031")	Output pressure	: 26.4Mpa ~ 46.8Mpa	Fan	: 40° ~ 65 °
Pump ratio	: Min. 66:1								
Nozzle orifice	: 482.6 μm ~ 787.4 μm (0.019" ~ 0.031")								
Output pressure	: 26.4Mpa ~ 46.8Mpa								
Fan	: 40° ~ 65 °								
<b>Typical Film Thickness</b>	<p>Recommended 500 μm dry. Depending on the purpose and the area of use, different film thickness may be applied.</p>								
<b>Subsequent Coat</b>	<p>According to specification.</p>								
<b>Shelf Life</b>	<p>12 months</p>								
<b>Standard Packing Unit</b>	<p>22.5 L (EH3090-A : 15L , EH3090-B : 7.5 L)</p>								
<b>Remarks</b>	<p>Do not store at temperature below 5 °C/41 °F or above 40 °C/104 °F. Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.</p>								
<b>Issued</b>	<p>July 2011</p>								

---

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

